

Nano EcoLine

Renovation (Matt & Gloss)

What is it?

Nano EcoLine Renovation is an advanced SiO₂-based renovation coating, developed to restore weathered surfaces without repainting or masking. Suitable for aluminium and plastics (weathered/chalked) and for painted surfaces that have been exposed to UV for long periods.

Key benefits

- Restores weathered surfaces (e.g., aluminium frames, façade panels and plastic components).
- No repainting required – saves time, cost and labour.
- Choice of matt or gloss finish.
- High stain and dirt resistance (e.g., oil, wine, lemon juice; depending on substrate and coating build-up).
- Graffiti- and stain-resistant; easy-clean effect.
- Fast curing – dust-dry within minutes; fully cured after approx. 24 hours.
- For manual application, the product can optionally be diluted with IPA (e.g., as a primer layer for hydrophobicity).

Applications

- Weathered aluminium frames and façade panels.
- Plastic cladding, PVC and Trespa® (HPL).
- Painted/spray-coated surfaces and industrial objects.
- Mineral substrates: stone, concrete and rough mineral surfaces (not suitable for polished substrates; abrade/matt first).
- Outdoor furniture (plastic or aluminium), caravans, campers, boats and construction equipment.

Coverage, storage and shelf life

- Application temperature: +5 to +40 °C.
- Coverage: approx. 20–100 m² per litre (depending on substrate, dilution and number of coats).
- Durability: approx. 5 years+ (depending on exposure/substrate).
- Storage: +5 to +25 °C.
- Shelf life (unopened): 12 months.

Instructions

Surfaces must be dry and free from dust, wax, oil, grease and other contaminants. Application should take place in a shaded and well-ventilated area.

Manual application

- Always test a small area before treating the entire surface.
- Open the bottle and pour the required amount onto a black microfibre cloth.
- Wrap this cloth around the (blue) application sponge.
- Apply evenly using linear strokes.
- For larger areas, the product can also be applied with a paint roller.
- For manual application, the product can optionally be diluted with isopropyl alcohol (IPA).

HVLP spraying

- Preferably apply to the final product after tests have been carried out and optimal parameters have been determined.
- HVLP spray gun with 0.8 mm nozzle is recommended.
- Spray distance: 35–50 cm (depending on parameters).
- Spray pressure: 5–6 bar (depending on parameters).
- Apply as a fine mist in the required amount.

Nano EcoLine

Renovation (Matt & Gloss)

Technical data

Property	Value / description
Technology	SiO ₂ -based renovation coating
Finish	Matt or gloss (variant depending on application)
Curing	Dust-dry within minutes; fully cured after approx. 24 hours
Dilution	Optional with IPA (manual application/primer layer)
Application (HVLP)	0.8 mm nozzle 35–50 cm 5–6 bar
Coating build-up	1–3 coats possible (depending on desired protection and substrate)

Physico-chemical properties

Property	Value
Flash point	17 °C DIN ISO 3679
Density	1,1 g/cm ³ DIN 12791 ISO 649
Viscosity	~ 23 mPa·s ISO 2555
Flow time	~ 26 s (3 mm) 3 DIN 53211
Colour	cloudy
Odour	mild irritant.
Water solubility	not miscible

Packaging units

Finish	Article number	Content	Packaging type
Gloss	CM.RENG/1L	1.0 L	Bottle
Gloss	CM.RENG/5L	5.0 L	Jerrycan
Matt	CM.RENM/1L	1.0 L	Bottle
Matt	CM.RENM/5L	5.0 L	Jerrycan

Safety instructions

- Read the Safety Data Sheet (SDS) before use.
- Highly flammable liquid and vapour; keep away from heat, sparks and open flames.
- Causes skin irritation and serious eye damage; wear suitable PPE.

PPE and workplace

- Wear chemical-resistant gloves, protective clothing and eye/face protection.
- Ensure an eyewash station/washing facilities are available in the work area.

Nano EcoLine

Renovation (Matt & Gloss)

Professional notes

- Professional use recommended; work according to your own risk assessment and test area.
- Prevent electrostatic discharge and ensure good ventilation.

Disposal

- Dispose of product and packaging residues in accordance with local regulations; dispose of contaminated residues via an authorised processor.

Transport information

- Transport indication: UN 1263 (Paint), class 3, packing group II (refer to SDS for details).

Disclaimer

The technical information in this document is based on product specifications, tests and practical experience. Because application, substrate and conditions are beyond NanoEnzo's control, the user must always assess suitability and carry out a test area. NanoEnzo accepts liability only for the quality of the delivered product at the time of delivery.